

Preparation of Nano Natural Dyes from the Flower of *Russelia Equisetiformis* and Applying on Fabrics using Mordants

¹Dr.M.Kumaresan, ²P.Balasubramaniam, ³E.Dhanasekaran, ⁴N.Sudha
¹Professor and Head, ^{2,3,4}Assistant Professor, Department of Chemistry
Erode Sengunthar Engineering College,
Thudupathi, Erode, Tamilnadu, India PIN 638 057

Abstract

The present scenario is focused more towards the utilization of the vast diversity of natural resources of color pigments for their use in food materials, pharmaceuticals and textiles, in place of their synthetic counterparts. This trend is aimed at safeguarding human health as well as protecting and prolonging life on earth. Due to increasing awareness of environmental issues and also pollution produced by synthetic dyes, wide spread interest has emerged in the dyeing of textile fibres using natural colorants on account of their better biodegradability and higher compatibility. This research aim is to extract the eco-friendly natural dye obtained from the flower of *Russelia equisetiformis* apply on silk fabrics using single mordants. The fastness properties of the flower of *Russelia equisetiformis* dyed silk fabrics have been studied using different concentrations (1%, 2% and 3%). The wash, rub, light and perspiration fastness of the dyed samples have been evaluated. The constituents present in the flower of *Russelia equisetiformis* are determined by using GC-MS analysis. The same procedure is repeated for the nano natural dyes obtained from the same plant parts. From the Comparison of these studies which helps the large scale preparation of the natural dye.

Keywords— Cotton, Silk Fastness, Mordants, Natural dye, *Russelia equisetiformis*

I. INTRODUCTION

Environmental pollution due to the discharge of dyeing industry effluents is the matter of major concern now-a-days. Until about 150 years ago all dyes were natural substances, derived mainly from plants and animals. Upto the end of 19th century natural dyes were the main colourants for textiles. Recently, interest in the use of natural dyes has been growing rapidly due to the result of stringent environmental standards imposed by many countries in response to toxic and allergic reactions associated with synthetic dyes [1]. The natural dyes present in plants and animals are pigmentary molecules [2] which impart colour to the materials. With the world becoming more conscious towards ecology and environment, there is greater need today to revive the tradition of natural dye and dyeing techniques as an

alternative of hazardous synthetic dyes is an extremely crude.

There are several plants/plant parts that provide natural dyes which are used in the textile industry. However, the common drawbacks of natural dyes are their non-reproducible and non-uniform shades, poor to moderate colour fastness and lack of scientific information on the chemistry of dyeing and standardised dyeing methods[3,4]. Many reports are available on application of natural dyes on silk[5,6] and cotton [7,8].

The aim of present work has been carried out to prepare eco-friendly natural dyes from the flower of *Russelia equisetiformis* and apply them on cotton and silk fabrics. In the present work an attempt has been made to study the effect of mordanting and dyeing properties [9] of cotton and silk fabrics such as, washing, rubbing, light fastness and perspiration [10] and also to visualize the effect of myrobolan and metallic mordants have been undertaken.

II MATERIALS AND METHODS

A. Materials

Loom state silk (430 ends/ dm,212 picks/dm,50g/m²) fabrics obtained from Gandhi Trust, Dindugal, was used for this study. Analytical reagents (AR) grade ferrous sulphate, aluminium sulphate, nickel sulphate, potassium dichromate, stannous chloride, commercial grade acetic acid, common salt, sodium carbonate were used. A natural mordant myrobolan (*Terminalia chebula*) powder was used for the study. Depending upon the mordant used, the colour obtained on textiles the flower of *Russelia equisetiformis* extract may give different shades. The myrobolan (harda) powder was soaked in water (1:10 volume) for overnight (12h) at room temperature to obtain the swelled myrobolan gel. It was then mixed with a known volume of water and heated at 80°C for 30 min. The resulting solution is cooled and filtered. The filtrate was used as final mordant solution for mordanting [11].

III. METHODS

A. Extraction of Colour Component

For optimizing the extraction method the ethanol extraction of dye liquor was carried out under varying conditions, such as time of extraction, temperature of extraction bath and material-to-liquor ratio. In each case, the optical density or absorbance value at a particular maximum absorbance wavelength ($\lambda_{420\text{nm}}$) for the ethanol extract of plant parts were estimated by using Hitachi-U-2000 UV-VIS absorbance spectrometer.

B. Dyeing of silk fabrics with the extract of the flower of *Russelia equisetiformis*

The wetted out silk samples were entered into dye baths containing required amount of dye extract and water. After 10 minutes, required amount of sodium carbonate and sodium chloride were added. The dyeing was carried out for one hour at 60°C. The dyed samples were dried in air without washing to make them ready for pre, simultaneous and post-mordanting using myrobolan and metallic salts.

C. Pre-Mordanting of silk fabrics with myrobolan and metallic salts

Bleached silk fabrics with or without pre-mordanting were further mordanted prior to dyeing using 1-3% of any one of the chemical mordants, such as aluminium sulphate, nickel sulphate, potassium dichromate, stannous chloride, copper sulphate and the myrobolan, at 60°C for 30 min with material-to-liquor ratio of 1:20. The samples treated with metal salts were dyed with the dye extract.

D. Simultaneous -Mordanting of silk fabrics with myrobolan and metallic salts.

Bleached silk fabrics were treated with both dye extract and metal salts simultaneously, using 1-3% of any one of the chemical mordants, such as aluminium sulphate, nickel sulphate, potassium dichromate, stannous chloride, copper sulphate and the myrobolan, at 60°C for 30 min with material-to-liquor ratio of 1:20.

E. Post-Mordanting of silk fabrics with myrobolan and metallic salts.

Bleached silk fabrics were dyed with dye extract. The wetted out cotton and silk samples were entered into different dye baths containing required amount of dye extract and water. After 10 minutes required amount of sodium sulphate was added. After 20 minutes required amount of sodium chloride was added. The dyeing was carried out for one hour at 50°C. The dyed samples were taken out, squeezed and used for treatment with metal salts process without washing. The dyed silk samples were treated with different metal salts using 1-3% of any one of the chemical mordants, such as aluminium sulphate, nickel sulphate, potassium dichromate, stannous

chloride, copper sulphate and the myrobolan, at 60°C for 30 min with material-to-liquor ratio of 1:20.

In all the above three methods, after the dyeing is over, the dyed samples were repeatedly washed with water and then dried in air. Finally, the dyed samples were subjected to soaping with 2gpl soap solution at 50°C for 10 min, followed by repeated water wash and drying under sun.

F. Determination of surface colour strength¹² (K/S value)

The K/S value of the undyed and dyed cotton and silk fabrics was determined by measuring surface reflectance of the samples using a computer-aided Macbeth 2020 plus reflectance spectrophotometer, using the following Kubelka Munk equation with the help of relevant software:

$$K/S = \frac{(1 - R_{\lambda_{\text{max}}})^2}{2R_{\lambda_{\text{max}}}} = \alpha C_d$$

where K is the coefficient of absorption; S the coefficient of scattering; C_d , the concentration of the dye and $R_{\lambda_{\text{max}}}$ the surface reflectance value of the sample at a particular wavelength, where maximum absorption occurs for a particular dye/colour component.

G. Evaluation of Colour Fastness:

Colour fastness to washing of the dyed fabric samples was determined as per IS: 764 – 1984 method using a Sasmira launder-O-meter following Is-3 wash fastness method. The wash fastness rating was assessed using grey scale as per ISO-05-A02 (loss of shade depth) and ISO-105-A03 (extent of staining) and the same was cross-checked by measuring the loss of depth of colour and staining using Macbeth 2020 plus computer-aided colour measurement system attached with relevant software.

Colour fastness to rubbing (dry and wet) was assessed as per IS: 766-1984 method using a manually operated crock meter and grey scale as per ISO-105-A03 (extent of staining).

Colour fastness¹⁴ to exposure to light was determined as per IS: 2454-1984 method. The sample was exposed to UV light in a Shirley MBTF Microsals fade-O-meter (having 500 watt Philips mercury bulb tungsten filament lamp simulating day light) along with the eight blue wool standards (BS 1006: BOI: 1978). The fading of each sample was observed against the fading of blue wool standards (1-8). Colour fastness to perspiration assessed according to IS 971-1983 composite specimen was prepared by placing the test specimen between two adjacent pieces of fabrics of silk and cotton and stitched all among four sides. The sample was soaked in the test solution (acidic /alkaline) separately with MLR 1:50 for 30 minutes at room temperature. The sample was then placed between two glass plates of perspirometer under load of 4.5kgs (10 lbs). The apparatus was kept in the oven for four hours at 37±2°C. At the end of this period the specimen was removed and dried in air

at a temperature not exceeding 60°C. The test samples were graded for change in colour and staining using grey scales.

IV. RESULT AND DISCUSSIONS

The colour strength values of silk fabrics dyed with the flower of *Russelia equisetiformis* obtained in this study by using single mordanting method are presented and compared in Tables 1, 2 and 3. From the results, it was observed that 3% concentration of the dye obtained from the flower of *Russelia equisetiformis* showed better colour strength values. In all the three dyeing methods, simultaneous method gave excellent results. In all the three methods of dyeing, using two plant parts, the mordants ferrous sulphate and aluminium sulphate show excellent results. For dyeing of silk, 1%, 2% and 3% mordant concentrations were used for the present study. Among these three concentrations 3% mordant concentration gave better results. The colour fastness values of silk fabrics dyed with the flower of *Russelia equisetiformis* obtained in this study by using single mordanting method are presented and compared in Tables 4.

Similar results were obtained in the previous study reported by Das et al¹³. The present study shows excellent wash fastness (GS : 4) and light fastness (GS :4) when compared with Das et al¹⁴ study (WF : 2-3 and LF : 3). A better light fastness (GS : 8) was reported by Sharada devi et al¹⁵ in pre mordanting method.

V. CONCLUSION

From the study of fastness properties and colour strength of the dyed silk samples, the flower of *Russelia equisetiformis* in simultaneous mordanting method with 3% mordant combination gives better results. The same procedure is repeated for the nano natural dyes obtained from the same plant parts. From the Comparison of these studies which helps the large scale preparation of the natural dye.

ACKNOWLEDGEMENT

The authors are thankful to Mr P Santharaj, Department of Textile Processing, Erode Institute of Technology for his support in the analysis of fastness properties of the dyed samples of this work.

REFERENCES

- [1] Anitha, K and Prasad, S.N. Developing multiple natural dyes from flower parts of Gulmohur. Current Science. **2007**, 92(12). 1681-1682.
- [2] Sandeep Bains, Singh, O.P, Ganganpreet Goraya and Manpreet Kang. Dyeing of Cotton with Golden drop dye. Journal of the Textile Association. **2003**, 183-186.
- [3] Samanta, A.K, Singhee Deepali and Seethia Mitu. Colourage. **2003**, 50(10), 29.

- [4] Gulrajani, M, L and Gupta Deepti. Natural Dye and their Application to Textiles (Department of Textile Technology, IIT, Delhi). **1992**, 25.
- [5] Mahale, G, Sakshi and Sunanda, R.K. Indian J Fibre Text. Res. **2003**, 28, 86.
- [6] Katti, M, R, Kaur, R and Shrihari, N. Colourage. **1996**, 43(12), 37.
- [7] Senthikumar, P, Umasankar, P and Sujatha, B. Indian Text. J. **2002**, 112 (6), 15.
- [8] Saxena, S, Iyer, V, Shaikh, A, I and Shenai, V.A. Colourage. **1997**, 44(11), 23.
- [9] Anderson, B. Creative Spinning, Weaving and Plant Dyeing, Angus and Robinson, Singapore. **1971**, 24 -28.
- [10] Ashis Kumar Samanta, Priti Agarwal and Siddhartha Datta. Indian Journal of Fibre and Textile Research. **2007**, 32, 466-476.
- [11] Kumaresan, M. and Palanisamy, P.N. Dyeing of silk with the stem of *Achras sapota* using combination of mordants. International Journal of Applied Engineering Research. **2010**, 5(12), 2031-2037.
- [12] Kumaresan, M., Palanisamy, P.N. and Kumar, P.E. Dyeing of cotton and silk using flower of *Spathodea campanulata*: Effects of mordanting and colour fastness properties. Journal of Basic and Applied Scientific Research. **2011**, 1(8), 933-941.
- [13] Das, D, Maulik, S.R and Bhattacharya, S.C. Indian J. Fibre Textile Res. **2008**, 33, 163.
- [14] Das, D, Maulik, S.R and Bhattacharya, S.C. Indian J. Fibre Textile Res. **2007**, 32, 366.
- [15] Sharada Devi, A, Sumanthy, B.S and Katyayini, V.K.L.T. *Man Made Textiles India*, **2002**, 181.