

A Comprehensive Study on the use of Modified Binders in Bituminous Mixes

Aznar Hamid

Assistant Professor Geeta Engineering College, Haryana

Abstract

Investigations have been carried out in India and countries abroad to find out the properties of bitumen and bituminous mixes and the methods by which they can be improved to cope with the above defects of pavements and incorporate certain additives or blend of additives. These additives added to enhance the binders are called "Bitumen Modifiers," and the bitumen premixed with these modifiers is known as "Modified Bitumen." Modified bitumen's performance depends upon the degree of modifications and type of additives, and modification process used. The next renewal period is expected to extend by 50 percent in surfacing with modified bitumen compared to the normal period indicated for conventional bitumen. For example, if the normal renewal cycle is 4 years, this may be enhanced to 6 years in modified bitumen. Full-scale performance studies carried out under the aegis of Ministry of Road Transport and Highways, New Delhi, Central Road Research Institute, New Delhi, Highway Research Station, Chennai, Rubber Board, Kottayam, Gujarat Engineering Research Institute, Vadodara, and Kerala Public Works Department revealed that the use of Modified Bitumen in construction/ maintenance of bituminous roads is cost-effective when life cycle cost is taken into consideration. In a nutshell, the choice will ultimately depend upon the life cycle costing of overlays and renewals using ordinary bitumen and modified bitumen for prevailing traffic and climatic conditions. It will also depend upon the type of pavement constructed. The need for bituminous binders has been aroused due to the pavement failures. Pavement failures are one of the important issues in the entire pavement system.

Keywords - Bituminous mix, Marshall Test, Stability, Aggregates, zycotherm.

I. INTRODUCTION

Bitumen is a mixture of different organic materials, mostly of carbon and hydrogen. It is produced through the vacuum distillation of petroleum. The viscoelastic behavior changes with temperature from solid to fluid and by cooling back in the original consistency. The bitumen binder can go through various problems in the field, such as stripping from the aggregate, leading to cracking, rutting, depressions, potholes, etc. Thus the binders can be

Modified by adding an additive to enhance its various properties. This binder in which an additive is added to make it better in its performance is called Modified binder. Modified binders are those bituminous binders whose properties have been modified by the use of additives.

II. MATERIALS

Aggregate and bitumen are the basic ingredients of bituminous mixes. Further, based on particle aggregates' size, they are divided into coarse aggregates, fine aggregates, and filler fractions. Materials used in bituminous pavements are discussed below:-

A. Coarse Aggregate

Impact value, abrasion value, and crushing strength of coarse aggregates should be good enough to withstand the design loads within the design life span. All the stresses coming on the wheels are beard by coarse aggregates. Wear due to abrasion is also to be resisted by coarse aggregates. That portion of the mixture that is retained on 2.36 mm (No. 08) sieve according to the Asphalt Institute is termed coarse aggregates.

B. Fine Aggregate

In coarse aggregates between the particles, voids remain. Those voids need to be filled. Fine aggregates fill those voids which remain there. So to fill the voids of coarse aggregates is the main function of Fine aggregates. Crushed stone or natural sand generally is termed as fine aggregates.

C. Filler

After the voids are filled in coarse aggregates by fine aggregates, some of the voids remain unfilled. The function of the fillers is to fill up the voids. Fillers used maybe stone dust, concrete dust.

D. Bitumen

Bitumen is used as a water repellent material.

III. BACKGROUND

The past decade (2001-10) marked a major surge in the use of modified bitumen for roads and airports, especially the use of crumb rubber modified bitumen (CRMB) and polymer modified bitumen (PMB). The Indian Roads Congress (IRC) brought out a special publication (IRC: SP:53) in 1999 to provide tentative guidelines on using modified bitumen in road construction. Although that publication had four



different specifications for PMB (elastomer), PMB (plastomer), CRMB, and natural rubber modified bitumen (NRMB), unfortunately, it was implied that their performance was equal in the absence of any recommendations for their use for specific traffic and/or climatic conditions. In another setback, IRC: SP:53 was revised in 2010 with one notable feature. The specifications for different modified binders were unified into one specification irrespective of the modifier type or its concentration. The minimum elastic recovery requirement was reduced for all modified binders, including PMB, with an elastomer to accommodate the CRMB.

Fortunately, most progressive contractors are not using the downgraded 2010 version of IRC: SP:53; they would rather use PMB with elastomer, which meets the enhanced elastic recovery requirement as in the 1999 version of the IRC: SP:53.

There is gross inadequacy of published data in India on relative field performance with and without different binder modifications under typical loading, climate, and combinations. Until relative field performance data is obtained in India, there is no other recourse but to rely on similar data or experience in the developed country.

IV. OBJECTIVE

The main objectives of this investigation are:

- To compare the Marshall properties modified samples with the conventional sample.
- To analyze the Marshall tests of modified binder mixes for deciding the optimum binder content (OBC) and best modifier for further studies.
- To study the characteristics of modified bitumen with the nano-material as additive.

V. SUMMARY

Since the asphalt concrete pavements go under failure problems at different temperatures and moisture conditions, many scientists and researchers used different kinds of materials and various methods to improve the properties. So it became necessary to provide the best possible way to get rid of these failure problems. In this study, zycotherm nano-material at three different percentages by weight of binder is used with three binder contents in the mixes, and later the properties were investigated. As a result, the addition of zycotherm has changed the properties to a great extent. From these results, it can be concluded that rutting and fatigue problems are decreased to a great range.

REFERENCES

- [1] Hurley GC, Prowell BD. Evaluation of Evotherm_ for the use in warm mix asphalt. National Center for Asphalt Technology. NCAT report 06-02, Auburn., (2006).
- [2] Elsa Sanchez-Alonso, Evaluation of compatibility and mechanical properties of bituminous mixes with warm additives Department of Transport, Projects and Process Technology, School of Civil Engineering (E.T.S.I.C.C.P.), University of Cantabria (UC), Avenida de los Castros/n.39005 Santander, Cantabria, Spain., (2012).
- [3] Dr. Hamed M. Jassim, Omar T. Mahmood, Sheelan A. Ahmed, Optimum Use of Plastic Waste to Enhance the Marshall Properties and Moisture Resistance of Hot Mix Asphalt, International Journal of Engineering Trends and Technology (IJETT), 7(1) (2013) 18-25.
- [4] Kapil Kushwah, Harswaroop Goliya and Mayur Singi EVALUATION OF SASOBIT WARM MIX ASPHALT advanced in civil engineering and applied mechanics,
- [5] Liantong mo, Xun li, Xing fang M. Huurman, Shaopeng w, laboratory investigation of compaction characteristics and performance of warm mix asphalt containing chemical additives, state key laboratory of silicate materials for architectures, Wuhan university of technology, Wuhan 430070, china technology & development, bam wegen bv, utrecht 3500 gk, the Netherlands., (2012).
- [6] Adriana, V., and David, H. T., Rutting characterization of warm mix asphalt and high RAP mixtures. Road Materials and Pavement Design., 13(1), (2012), 1-20.
- [7] Ahmed, T. A., Elie Y. H., Sebaaly, P. E., and Nate, M. Influence of Aggregate Source and Warm-Mix Technologies on the Mechanical Properties of Asphalt Mixtures. Advances in Civil Engineering Materials, 2(1) (2013), 400–417.
- [8] PROWELL B.D., HURLE G.C.: Warm-Mix Asphalt: Best Practices. Quality Improvement Series 125, NAPA, Lanham, United States, 2007. BEUVING E.: The use of Warm Mix Asphalt in Europe and the USA. Conference Asfaltové vozovky., (2011).
- [9] České Budějovice 2011 WILLIS J., ET AL.: Combining Warm Mix Asphalt Technologies with Mixtures Containing Reclaimed Asphalt Pavement. Proceedings 2nd International Warm-mix Conference (prezentace), St. Louis, 2011. EPPS A., ET AL.: Moisture Sensitivity of WMA – A review and look to the future. Proceedings 2nd International Warm-mix Conference (prezentace), St. Louis, 2011. OLARD F., ET AL.: Laboratory assessment of mechanical performance and fume emissions of LEA® HWMA (90°C) vs. traditional HMA (160°C). Proceedings 2nd International Warm-mix Conference, St. Louis, 2011. VALENTIN, J., SOUKUPOVA, L., MORAL, X., BENES, J., CÁPAYOVÁ, S.: Posouzení experimentálně vyrobených a průmyslově vyvíjených 70 alternativ nízkoviskózních asfaltových pojiv - charakteristiky asfaltových pojiv, charakteristiky směsi ACO 11+. Dílčí výzkumná zpráva 1.1.5, Centrum CESTI, FSv.
- [10] ČVUT v Praze, (15 stran). ČSN EN 14023. Asfalty a asfaltová pojiva - Systém specifikace pro polymerem modifikované asfalty. Praha: Český normalizační institut, 2006. ČSN EN 14770. Asfalty a asfaltová pojiva - Stanovení komplexního modulu ve smyku a fázového úhlu - Dynamický smykový reometr (DSR). Praha: Český normalizační institut, 2006. ČSN EN 1427. Asfalty a asfaltová pojiva: Stanovení bodu měknutí - Metoda kroužek a kulička. Praha: Český normalizační institut, 2007. ČSN EN 1426. Asfalty a asfaltová pojiva: Stanovení penetrace jehlou. Praha: Český normalizační institut., (2007).
- [11] K. Kiruthiha, G. Loshini, M. Thivya, Mr. Vignesh Kumar Strengthening of Flexible Pavement using Egg Shell as a Filler, International Journal of Engineering Trends and Technology (IJETT), 21(10) (2015) 483-486.
- [12] ČSN EN 13302. Asfalty a asfaltová pojiva - Stanovení dynamické viskozity. Praha: Český normalizační institut, 2010. ČSN EN 13398. Asfalty a asfaltová pojiva - Stanovení vratné duktility modifikovaných asfaltů. Praha: Český normalizační institut, 2010. ČSN EN 13589. Asfalty a asfaltová pojiva - Stanovení tažných vlastností

- modifikovaných asfaltů metodou silové duktility. Praha: Český normalizační institut, 2004. AASHTO Designation: T 283-03. Standard Method of Test for: Resistance of Compacted Asphalt Mixtures to Moisture-Induced Damage. January 2007. Washington: American Association of State and Highway Transportation Officials., (2007). ČSN EN 12697-12.
- [13] Asfaltové směsi – Zkušební metody pro asfaltové směsi za horka: Část 12: Stanovení odolnosti zkušebního tělesa vůči vodě. Březen 2005. Praha: Český normalizační institut, 2005. ČSN EN 12697-26. Asfaltové směsi – Zkušební metody pro asfaltové směsi za horka – Část 26: Tuhost. Praha: Český normalizační institut, 2012. ČSN EN 12697-44. Asfaltové směsi – Zkušební metody pro asfaltové směsi za horka – Část 44: Šíření trhliny zkouškou ohybem na půlválcovém zkušebním tělese. Praha: Český normalizační institut, 2011. TP 151. Asfaltové směsi s vysokým modulem tuhosti (VMT). Ministerstvo dopravy, odbor silniční infrastruktury, 2010. ČSN EN 12697-23. Asfaltové směsi – Zkušební metody pro asfaltové směsi za horka: Část 23: Stanovení pevnosti v příčném tahu. Březen 2005. Praha: Český normalizační institut., (2005).